



# OMEGA II

## Direct Metallization Processing Steps Vertical Mode

<u>PROCESS STEPS</u>	<u>TEMPERATURE</u>	<u>TIME</u>
1.) Cleaner, Conditioner <b>CC-131</b>	60°C to 65°C	5 to 7 minutes
2.) Water Rinse	Room Temperature	1 to 2 minutes
3.) Pre-Dip <b>PD-155</b>	Room Temperature	1 to 2 minutes
4.) Catalyze <b>CT-160</b>	43°C to 46°C	5 to 7 minutes
5) Water Rinse	Room Temperature	1 to 2 minutes
6.) Water Rinse	Room Temperature	1 to 2 minutes
7.) Accelerate <b>AC-171</b>	60°C to 65°C	5 to 7 minutes
8.) Water Rinse	Room Temperature	1 to 2 minutes
9.) 5% Sulfuric Acid	Room Temperature	1 to 2 minutes
10.) Water Rinse	Room Temperature	1 to 2 minutes
11.) Water Rinse	Room Temperature	1 to 2 minutes
12.) Dry & Image or Panel Flash		

